



TECHNICAL DATA SHEET

www.micromod.de
Telephone: + 49 381 / 7999 7000
Fax: + 49 381 / 7999 7070
E-mail address: info@micromod.de

micromod Partikeltechnologie GmbH
Schillingallee 68
D-18057 Rostock
Germany

| | |
|--------------------------------------|---|
| Product code: | 09-56-132 |
| Product name: | nanomag@-D |
| Surface: | PEG-COOH |
| Size: | 130 nm |
| Solid content: | 10 mg/ml |
| Composition: | dextran iron oxide composite particles |
| Polydispersity index: | < 0.200 |
| Shape: | cluster-typed |
| Density: | 2.5 g/ccm |
| Magnetization: | 53 Am ² /kg iron (H = 80 kA/m) |
| Saturation magnetization: | >75 Am ² /kg iron (H > 800 kA/m) |
| Coercive field H_c: | 0.444 kA/m |
| Stable in: | aqueous buffers pH > 4 |
| Not stable in: | organic solvents, acidic solutions pH < 4 |
| Product form: | Suspension in water |
| Particles per ml: | 3.5 E12 |
| Particles per mg: | 3.5 E11 |
| Colour: | dark brown |
| Additional remarks: | Storage at 2 - 8 °C for 6 months. |